

Polyvin BHGE 12/820/1039

Characteristics	Standard	Units	Values
Density at 20°C	ISO 1183	kg/dm ³	1,52
Shore D hardness	ISO 868	Shore D	79
Vicat softening temperature	ISO 306 B 50	°C	82,0
Flexural E Modulus	ISO 178	Mpa	-
Charpy impact strength at 23°C	ISO 179 1eA	kJ/m ²	12
Traction at 23°C	ISO 527-2		
<u>Yield stress</u>	<u>Mpa</u>	<u>> 40</u>	
Elongation at break		%	> 120
Oxygen Index	ISO 4589-2	%	54,0
Coefficient of Expansion	ISO 7991	K.1	5,5E-05
Colour	white, other colours possible		
Stabilizer	Lead		

Bankverbindung: Dresdner Bank Hamburg
Konto No.: 05 759 705 00, BLZ 200 800 00
SWIFT Code: DRESDEFF200

Handelsregister Nr.: HRB 576 35
Geschäftsführer: T.-A. Harde
Ust.-Id.Nr. DE 811802467